

PHX-PVC 80 Mil Data Sheet

Product Description:

Phoenix PVC 80 mil Single-Ply Membrane is a resin based sheet with reinforced anti-wicking polyester scrim for added water resistance and strength. Our formulation includes pigments, plasticizers, fillers, and stabilizers exceeding ASTM D-751/D-4434. Available in White, Tan, Grey, Dark Brown, Solar Reflective (SR) Tan, and Solar Reflective (SR) Grey.

Packaging:

Size Sq. Ft. / Weight per roll (approx.)

6' x 60' 360 sq. ft. / 193 lbs.

3' x 60' 180 sq. ft. / 96 lbs.

Features:

- Heat welded seams provide superior seam strength
- Specially Formulated for ponding water
- Exceeds Energy Star[™] and California Title 24 requirements for Solar Reflectance and Emissivity
- Every warranty is a No Dollar Limit (NDL) and 100 percent Non-Prorated warranty

Warranties:

- Up to 30-Year Limited Commercial Material Warranty
- Residential Lifetime Material only Warranty
- Warranty Advantage and Total warranties System option for Authorized installer
- All warranties are Transferable

Membrane Color	Thickness in Mil	Solar Reflectant	Thermal Emittance	SRI Value	SRI Value 3-year	<u>LRV</u>
White	50,60,80	0.870	0.88	110	91	94.3
SR Tan	60	0.770	0.87	95	78	69.7
SR Grey	60	0.770	0.87	95	75	67.2
Tan	50,60,80	0.366	0.87	39	N/A	30.2
Brown	60	0.079	0.87	2	N/A	7.2
Grey	50,60,80	0.163	0.88	13	N/A	18.1

Property	<u>Test</u>	Requirement	80 Mil	
Overall thickness of PVC sheet, min. (in.	ASTM D751	0.072	0.080 nom	
Breaking strength, min. (lbf/in.)	ASTM D751	240	Pass	
Elongation at the break, min. %	ASTM D751	20	Pass	
Retention of properties after heat aging (min. % of original):	ASTM D4434	90	Pass	
Tearing strength, min. (lbf	ASTM D751 ASTM D4434	45	Pass	
Low temperature bend	ASTM D2136	-40°F	Pass	
Accelerated weathering Cracking (7x magnification) Crazing (7x magnification)	ASTM D4434	None None	Pass	
Dimension stability, max %	ASTM D1204	0.5	Pass	
Change in weight after immersion in water, max %	ASTM D570	3.0	1.5 nom	
Static puncture resistance	ASTM D5602	33	Pass	
Dynamic puncture resistance	ASTM D5635	14.7	Pass	